

TEST REPORT

Number: TWNT00581876

Applicant:

Date: OCT 12, 2010

Sample Description :

One (1) piece of submitted sample said to be Nylon ripstop woven fabric with White PU finish, 70Dx210D, in Black.

Applicant's Provided Care Instruction/Label : -

Date Received/Date Test Started : OCT 05, 2010

Standard : -

Style/Article No. : -

Order No. : RG2724

Buyer's Name : -

Agent's Name : -

Brand Name : -


Ref. : -

Conclusion:

The submitted sample meets the requirements stated in National Fire Protection Association no. 701 small scale for fire tests of Flame Resistant textiles & films.

Remark : Fabric weight : 4.8 oz/yd²

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited



Carol Peng
Director
Textile And Footwear Division

Tina/Sakura

Page 1 Of 2

Intertek Testing Services Taiwan Ltd.

8F., No. 423, Ruiguang Rd., Neihu District, Taipei 11492, Taiwan, R.O.C.

全國公證檢驗股份有限公司

11492 台北市內湖區瑞光路 423 號 8 樓

Tel: (+886-2) 6602-2000 · 2797-8885 Fax: (+886-2) 6602-2400 · 6602-2401



Number: TWNT00581876

Tests Conducted (As Requested By The Applicant)

1 Fire Test For Flame - Resistant Textiles And Films (NFPA 701-1989 Small Scale Test):

Requirements:

1. Material shall not continue flaming for more than two seconds after the test flame is removed from contact with the specimen.
2. Char length – 6.5 inches maximum for any specimen
- 5.5 inches maximum for average of 10 specimens
3. Portions or residues of textile or films which break or drip from the test specimen shall not continue to flame after they reach the floor of the test.

Test Results:

Specimen	Char Length (Inch)	After Flame Time (Second)	Residual Flame Time (Second)
1.	5.4	NIL	NIL
2.	5.0	NIL	NIL
3.	4.8	NIL	NIL
4.	4.1	NIL	NIL
5.	4.5	NIL	NIL
6.	4.1	NIL	NIL
7.	4.7	NIL	NIL
8.	5.0	NIL	NIL
9.	4.7	NIL	NIL
10.	4.7	NIL	NIL
Average.	4.7		

Remark : Fabric Weight : 4.8 oz/yd²

Weight Of Material Being Test (oz/yd ²)	Maximum Average Of 10 Specimens (Inch)	Maximum Individual For Each Specimens (Inch)
Over 10	3.5	4.5
Over 6 And Not Exceeding 10	4.5	5.5
Not Exceeding 6	5.5	6.5